



Natural Latex PF 240

Powder Free Ambidextrous Non-Sterile 24 cm Textured Natural Rubber Latex Gloves

Registered as PPE Category I (Simple Design) according to Council Directive 89/686/EEC

PRODUCT INFORMATION

| Size | Catalogue Numbers | Applicable Norms with Pictograms | | |
|--------------------|-------------------|---|--|------------------------|
| Extra Small (XS/6) | 62 4121 | | | For minimal risks only |
| Small (S/7) | 62 4122 | | | |
| Medium (M/8) | 62 4123 | | | |
| Large (L/9) | 62 4124 | EN420: 2003 | | |
| | | Also meets or exceeds EN455-1, 2 & 3:2000 relating to Council Directive 93/42/EEC for Medical Devices | | |

Material: Natural Rubber Latex. Contains 50 micrograms or less of total water extractable protein per gram, using the EN455-3: 2000/ ASTM D5712-05 Modified Lowry Method.

Design: Natural colour, ambidextrous, beaded cuff and fully textured.

Packaging: Hundred & Fifty (150) gloves per natural carton dispenser. Gloves are flat-packed. Ten (10) dispensers per case. Recycle carton only.

PHYSICAL PROPERTIES

| Characteristics | Value | Test Method |
|--------------------|----------------------|---------------|
| Freedom from holes | 1.5 AQL ¹ | EN374-2: 2003 |

¹AQL as defined per ISO 2859 for sampling by attributes

| Tensile Properties | Tensile Strength (min) Typical | | Ultimate Elongation | |
|---------------------------|--------------------------------|-------|---------------------|---|
| - Before Aging | 9.0N, min. | >9.0N | 700%, min. | EN455-2: 2000, ASTM D 412-06a and ASTM D3578-05 |
| - After Accelerated Aging | 6.0N, min. | >9.0N | 500%, min. | |

| Dimensional | Measured Point | Mm | mil | |
|---------------------|----------------|------|----------------|----------------------------------|
| - Nominal Thickness | Middle Finger | 0.13 | 5.1 | ASTM D 3767-03 and ASTM D3578-05 |
| | Palm | 0.10 | 3.9 | |
| | Cuff | 0.08 | 3.1 | |
| - Length | 240mm, min. | | 245mm, typical | EN420: 2003 |

Palm Widths

| | | | | | |
|----------------------|------|-----|-----|-----|---------------|
| - Nominal Width (mm) | XS/6 | S/7 | M/8 | L/9 | EN455-2: 2000 |
| | ≤80 | 85 | 95 | 105 | |

Hand Circumference

| | | | | | |
|------------------------------|------|-----|-----|-----|-------------|
| - Nominal circumference (mm) | XS/6 | S/7 | M/8 | L/9 | EN420: 2003 |
| | 152 | 178 | 203 | 229 | |

ADDITIONAL DATA

- Biocompatibility demonstrated by the Primary Skin Irritation Test CPSC 16-II-1500 and dermal sensitization test ASTM F-720-81
- Free of Thiazoles and Thiurams - these chemical accelerators are excluded from the manufacturing process.
- Powder free to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical), with a limit of 2.0 mg/glove (ASTM D6124-06 “Standard Test Method for Method for Residual Powder on Medical Gloves)
- Fit for special purpose - Size and Length: Size 9 (L) gloves are shorter in length than that required by EN420:2003. These gloves are intended for use in light-duty manufacturing and industrial applications, where the demand for the advantages of a shorter gloves outweigh the need for additional length.
- Ecological - 50% more products in the same volume to limit CO2 emissions and save space storage. Ink on the packaging reduced by 30%. Recycled carton only. Supply Chain optimized to reduce CO2 emission by more than 15% to deliver our products.

QUALITY SYSTEMS

- Manufactured in accordance with ISO 9001:2000 and ISO 13485:2003.

“ecoSHIELD™, Protect Your Future”



www.shieldscientific.com

ecoSHIELD™ is a trademark of SHIELD Scientific. © 2007 Copyright SHIELD Scientific B.V. - All Rights reserved

Galvanistraat 1 • 6716 AE EDE • The Netherlands - Phone +31 (0)318 754 141 • Fax +31 (0)318 503 742 • E-mail: Info@shieldscientific.com