



Powder Free Extra Length Ambidextrous Non-Sterile 30 cm Textured Latex Gloves

PPE Category III (Complex Design) according to Council Directive 89/686/EEC

Fully compliant to the latest PPE norms - EN374: 2003 "Protective gloves against chemicals and micro-organisms"

PRODUCT INFORMATION

Size	Catalogue Numbers	Applicable Norms with Pictograms			
Extra Small (XS/6)	67 4251	EN374-1 :2003 	EN374-2:2003 LEVEL 3		 0120*
Small (S/7)	67 4252				
Medium (M/8)	67 4253				
Large (L/9)	67 4254	EN420: 2003			
Extra Large (XL/10)	67 4255	Also meets or exceeds EN455-1, 2 & 3:2000 relating to Council Directive 93/42/EEC for Medical Devices			

* SGS United Kingdom Limited (Notified Body No: 0120), Camberley, Surrey, GU15 3EY, UK

Material: Natural Rubber Latex. Contains 50 micrograms or less of total water extractable protein per gram, using the EN455-3: 2000/ ASTM D5712-05 Modified Lowry Method. Typical measurements for latex protein are $\leq 30\mu\text{g/g}$ as per Modified Lowry Method.

Design: Natural colour, ambidextrous, beaded cuff and fully textured

Packaging: Fifty (50) gloves per dispenser. Dispenser is varnished for enhanced compatibility with laboratory environments. Gloves are flat-packed. Ten (10) dispensers per case. Packed in a double-walled shipping case.

PHYSICAL PROPERTIES

Characteristics	Value	Test Method
Freedom from holes	<0.65 AQL ¹	EN374-2: 2003

¹ AQL as defined per ISO 2859 for sampling by attributes

Tensile Properties	Tensile Strength (min) Typical		Ultimate Elongation	
- Before Aging	>9.0N, min.	>9.0N	700%, min.	EN455-2: 2000, ASTM D573-4 and ASTM D 412-06a
- After Accelerated Aging	>6.0N, min.	>9.0N	500%, min.	

Dimensional	Measured Point	mm	mil	
- Nominal Thickness	Middle Finger	0.14	5.5	ASTM D 3767-03
	Palm	0.12	4.7	
	Cuff	0.10	3.9	
- Length	300mm, min.		305mm, typical	EN420:2003

Palm Widths

- Nominal Width (mm) (+/- 5 mm)	XS/6	S/7	M/8	L/9	XL/10	EN455-2: 2000
	75	85	95	106	116	

Hand Circumference

- Nominal circumference (mm)	XS/6	S/7	M/8	L/9	XL/10	EN420: 2003
	152	178	203	229	254	

ADDITIONAL DATA

- Non-detectable levels of chemical allergens using aqueous solution extraction (Phosphate buffered solution) and High Performance Liquid Chromatography (HPLC) assay method for quantitative analysis.
- Biocompatibility demonstrated by the Primary Skin Irritation Test CPSC 16-II-1500 and dermal sensitization test ASTM F720-81.
- Free of Thiazoles and Thiurams - these chemical accelerators are excluded from the manufacturing process.
- Powder free to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical) with a limit of 2.0 mg/glove (ASTM D6124-06 "Standard Test Method for Residual Powder on Medical Gloves").
- Micro - organism and virus resistant - passes highest level of micro - organism resistance per EN374-2: 2003 (Performance level 3, AQL <0.65 and inspection level G1 according to 1000ml water test) and passes viral penetration test using Phi-X 174 bacteriophage (ASTM F1671-97b).

QUALITY SYSTEMS

- Manufactured in accordance with ISO 9001:2000 and ISO 13485:2003.

“SHIELDskin™, A revolution in Glove Technology”



www.shieldscientific.com

SHIELDskin™ is a trademark of SHIELD Scientific © 2007 Copyright SHIELD Scientific B.V. - All Rights reserved
Galvanistraat 1 • 6716 AE EDE • The Netherlands - Phone +31 (0)318 754 141 • Fax +31 (0)318 503 742 • E-mail: Info@shieldscientific.com